## 1763 GRANITE®

A hearty, weathered granite showing deep shades of earthen brown and amber. Split faces show a range of blush and blue-grays with some white swirls and striations.

## MATERIAL SPECIFICATIONS



BUILDING STONE	SIZE	FACING AREA	COVERAGE (Average)	PACKAGED WEIGHT	
Mosaic Pattern	Thickness 3" ± to 5" ±	1/4 sq. ft. to 3 sq. ft.	35-40 sq. ft. per ton	3,600-4,200 lbs. ±	
Roughly Squared/ Roughly Rectangular	Thickness 3" ± to 5" ±	1/4 sq. ft. to 3 sq. ft.	35-40 sq. ft. per ton	3,700-4,400 lbs. ±	
Ashlar	Thickness 3" ± to 5" ± Height 4" ± to 12" ±	1/4 sq. ft. to 2 sq. ft.	35-40 sq. ft. per ton	3,600-4,400 lbs. ±	
Ledge Stone	Thickness 1" ± to 5" ±, Heig Length 4" ± to 12" ±	ht 3" ± to 5" ±	35 sq. ft. per ton	2,800-3,500 lbs. ±	
THIN VENEER	SIZE	FACING AREA	COVERAGE (Average)	PACKAGED WEIGHT	
Mosaic Pattern	Thickness ¾" ± to 1¼" ±	1/4 sq. ft. to 1¼ sq. ft.	160 sq. ft. dealer crate 10 sq. ft. consumer box	2,200-2,700 lbs. ± 140-150 lbs. ±	
Roughly Squared/ Roughly Rectangular	Thickness ¾" ± to 1¼"±	1/4 sq. ft. to 1¼ sq. ft.	160 sq. ft. dealer crate 10 sq. ft. consumer box	2,200-2,700 lbs. ± 140-150 lbs. ±	
Ashlar	Thickness ¾" ± to 1¼" ±	Height 3" ± to 5" ± Length 6" ± to 20" ±	160 sq. ft. dealer crate 10 sq. ft. consumer box	2,200-2,700 lbs. ± 🔳 140-150 lbs. ±	
Ledge Stone	Thickness ¾" ± to 1¼" ±, H Length 4" ± to 12" ±	eight 3" ± to 5" ±	160 sq. ft. dealer crate 10 sq. ft. consumer box	2,200-2,700 lbs. ± <b>II</b> 140-150 lbs. ±	
LANDSCAPING STONE*	SIZE	FACING AREA	COVERAGE (Average)	PACKAGED WEIGHT	
Irregular Flagging	Thickness 1" ± to 3" ±	1/2 sq. ft. to 3 sq. ft. ±	70 sq. ft. per ton	3,300-4,400 lbs. ± 🔳 ↑→	
Wall Stone	Thickness 4" ± to 12" ±	1/4 sq. ft. to 3 sq. ft. ±	12-14 cu. ft. per ton	3,400-3,900 lbs. ±	
Cottage Wall Stone	Thickness 3" ± to 8" ±	1/4 sq. ft. to 2 sq. ft. ±	12-14 cu. ft. per ton	2,800-3,300 lbs. ±	
Thin Wall Stone	Thickness 1" ± to 3" ±	1/4 sq. ft. to 1 sq. ft. ±	12-14 cu. ft. per ton	3,300-3,800 lbs. ±	
Garden Steppers	Thickness 3" ± to 5" ±	2 sq. ft. to 4 sq. ft. ±	35-40 sq. ft. per ton	1½ to 2 plus tons ±	
Step Slab Material	Thickness 5" ± to 8" ±	ing ±	1½ to 2 plus tons ±		
Landscape Boulders	Clusters of 50 lbs. to 300 lb	1½ to 2 plus tons ± 🔳			

\* Ticonderoga Granite<sup>™</sup> - a blend of Wood Creek Granite<sup>®</sup>, Crown Point Granite<sup>™</sup> and 1763 Granite<sup>®</sup>, is used for landscape applications.

📰 - Product ships in 4-sided crate. All others ship via low pallets. One trailer load = 12-15 low pallets.

↑→ - Indicates stone is stacked either vertically or flat.

## ASTM DATA AVERAGE RESULTS FOR TESTS C-97, C-99, AND C-170:

C-97		C-99		C-170		
WATER Absorption %	DENSITY: Pounds Per Cubic Foot	SPECIFIC GRAVITY	MODULUS OF RUPTURE PERPENDICULAR	MODULUS OF RUPTURE PARALLEL	COMPRESSIVE Strength Perpendicular	COMPRESSIVE Strength Parallel
0.19	165.5	2.65	2,498 psi	1,120 psi	29,000 psi	26,810 psi