Corinthian GRANITE®

Cool and Classic. An elegant, enduring, medium to coarse-grained granite featuring 70% Hudson River blue with a mixture of green, black, pink, brown, burgundy, and white. A small percentage of this granite has speckles throughout consisting of red and black garnet inclusions and quartz crystals.

MATERIAL SPECIFICATIONS



BUILDING STONE	SIZE	FACING AREA	COVERAGE (Average)	PACKAGED WEIGHT		
Mosaic Pattern	Thickness 3" ± to 5" ±	1/4 sq. ft. to 3 sq. ft.	35-40 sq. ft. per ton	3,700-4,300 lbs. ±		
Roughly Squared/ Roughly Rectangular	Thickness 3" ± to 5" ±	1/4 sq. ft. to 3 sq. ft.	35-40 sq. ft. per ton	3,700-4,400 lbs. ±		
Ashlar	Thickness 3" ± to 5" ± Height 4" ± to 12" ±	1/4 sq. ft. to 2 sq. ft.	35-40 sq. ft. per ton	3,600-4,400 lbs. ±		
Ledge Stone	Thickness 3" ± to 5" ±, Heig Length 8" ± to 12" ±	ht 3" ± to 5" ±	35 sq. ft. per ton	3,500-4,200 lbs. ±		
THIN VENEER	SIZE	FACING AREA	COVERAGE (Average)	PACKAGED WEIGHT		
Mosaic Pattern	Thickness 3/4" ± to 11/4" ±	1/4 sq. ft. to 1¼ sq. ft.	160 sq. ft. dealer crate 10 sq. ft. consumer box	2,200-2,700 lbs. ± 1 40-150 lbs. ±		
Roughly Squared/ Roughly Rectangular	Thickness 3/4" ± to 11/4"±	1/4 sq. ft. to 1¼ sq. ft.	160 sq. ft. dealer crate 10 sq. ft. consumer box	2,200-2,700 lbs. ± 目 140-150 lbs. ±		
Ashlar	Thickness ¾" ± to 1¼" ±	Height 3" ± to 5" ± Length 6" ± to 20" ±	160 sq. ft. dealer crate 10 sq. ft. consumer box	2,200-2,700 lbs. ± ■ 140-150 lbs. ±		
Ledge Stone	Thickness ¾" ± to 1¼" ±, H Length 8" ± to 12" ±	eight 3" ± to 5" ±	160 sq. ft. dealer crate 10 sq. ft. consumer box	2,200-2,700 lbs. ± ■ 140-150 lbs. ±		
LANDSCAPING STONE*	SIZE	FACING AREA	COVERAGE (Average)	PACKAGED WEIGHT		
Irregular Flagging	Thickness 1" ± to 3" ±	1/2 sq. ft. to 3 sq. ft. ±	70 sq. ft. per ton	3,300-4,400 lbs. ± ■ 1→		
Wall Stone	Thickness 4" ± to 12" ±	1/4 sq. ft. to 3 sq. ft. ±	12-14 cu. ft. per ton	3,400-3,900 lbs. ±		
Cottage Wall Stone	Thickness 3" ± to 8" ±	1/4 sq. ft. to 2 sq. ft. ±	12-14 cu. ft. per ton	2,800-3,300 lbs. ±		
Thin Wall Stone	Thickness 1" ± to 3" ±	1/4 sq. ft. to 1 sq. ft. ±	12-14 cu. ft. per ton	3,300-3,800 lbs. ±		
Garden Steppers	Thickness 3" ± to 5" ±	2 sq. ft. to 4 sq. ft. ±	35-40 sq. ft. per ton	3,700-4,400 lbs. ±		
Step Slab Material	Thickness 5" ± to 8" ±	1½ to 2 plus tons ±				
Landscape Boulders	Clusters of 50 lbs. to 300 lb	1½ to 2 plus tons ± ■				

^{*} Saratoga Granite™ - a blend of Corinthian Granite® and American Granite™, is used for landscape applications.

ASTM DATA AVERAGE RESULTS FOR TESTS C-97, C-99, C-170, AND C-880:

C-97		C-99		C-170		C-880		
WATER Absorption %	DENSITY: Pounds Per Cubic Foot	SPECIFIC GRAVITY	MODULUS Of Rupture Perpendicular	MODULUS Of Rupture Parallel	COMPRESSIVE Strength Perpendicular	COMPRESSIVE Strength Parallel	FLEXURAL Strength Seam Face	FLEXURAL Strength Split Face
0.17	172.3	2.68	2,559 psi	2,063 psi	21,392 psi	20,323 psi	7,581 psi	7,734 psi

II - Product ships in 4-sided crate. All others ship via low pallets. One trailer load = 12-15 low pallets.

[↑] - Indicates stone is stacked either vertically or flat.